

IPA PU Flüssigfolie

Crackbridging liquid Pu-membrane for waterproof concrete-coating

Product-description:

IPA Pu-Membrane is a high-elastic, tar-free 2-Component-Polyurethane-coating-material. IPA Pu-Membrane viscous is formulated for vertical applications.

Solventfree according to lbh-recommendation

Application-areas:

For balcony, parking- and bridge-structures to make high-elastic, waterproof, passable and nonskid coatings with feeded aggregate on concrete or cement-substrates, with existing cracks or where crack-formation is to be expected.

System-characteristics:

- High crackbridging abilities up to -20°C
- Abrasion- and chemical-resistant
- Weather resisting, protects from water- and chloride intrusion
- Durable and economic
- High layer-thickness with low material-consumption.
- Recoating after 2hrs. possible because of fast curing

Certificates:	EMPA (Switzerland)
Colours:	Sand-yellow, clear grey.
Shelf-life:	In original-unopened containers 1 year when stored in cool, dry areas

Resistance:

Chemically:

The membrane is permanently waterproof against watery chloride solutions, thinned detergent-solutions, soda-lye 2%, brake fluids, just as organic lubricates - and fuels. The Top-coat improves the resistance additionally.

Thermal:

Dry heat for a short time until $+ 80^{\circ}\text{C}$.

Processing:

Mixing advice:

Comp. I thoroughly stir up and then pour Comp. II completely in Comp. I. With electric stirrer, (300-400 rp/Min), or adequate mixing equipment, mix intensively.

The time of mixing amounts to at least 3 minutes. and is then finished, when a homogeneous mixture is obtained. Mixed material is to be poured into a clean vessel, and has to be mixed again shortly

Technical Data:

Mixing-Ratio:	IPA PU-MEMBRANE/IPA PU-MEMBRANE
VISCOUS:	89 parts by weight Comp. I 11 parts by weight Comp. II
Density:	1,015kg/dm ³
Curing-time	1-2 hours
Next coating (20°C)	from 2 hours on
Consumption according to system	0,7-2,0kg/m ²
Adhesion on pimer coating	> 1,5N/mm ²
Shore A hardness	68-78
Tensile Strength (20°C)	after 7d > 15N/mm ²
Tear Strength (20°C)	7d > 800%
Dynamic Crack bridging	(-20°C) maximum. 0,8mm
Packaging:	
IPA Pu-Membrane:	20 kg net
IPA Pu-Membrane viscous:	20 kg net.

Horizontal surfaces:

The mixed material is poured on the surface, and must be broadcasted with a teeth-trowel . Immediately backroll to relieve trapped air-bubbles. After waiting approximately. 5-10 minutes broadcast the fresh surface continuously with dry natural quartz-sand first cautiously and then in excess, within maximum. 30 minutes.

With direct sun-insulation or temperatures > 20°C immediately begin with broadcasting aggregates. Hint:

The broadcasting of aggregate is always to be controlled, to avoid a non uniform appearance of the surface because of lack of aggregate. Excess of liquid material at the surface gives a insufficient view of the coating.

Vertical surfaces

approximately. Apply 1,3 kg/m² " IPA Pu-Membrane viscous and broadcast 1 -2 kg/m² fine quartz-sands 0,1-0,3 mm .

Top-sealer or Top coat:

The top sealing with IPAPUR VS/Le as well as. the top-coating with IPAPUR GB are applied with notched squeegee or with a role.A slightly higher material-consumption is necessary by this method, however in favour of a better appearance and surface-performance.

IPA PU Flüssigfolie

Crackbridging liquid Pu-membrane for waterproof concrete-coating

Priming on surfaces exposed to weathering:

In order to get an optimal pore-closure, and to avoid air entrainment into the basic-layer, we recommend to prime 2 times on weathered-surfaces with IPAPOX B/DB.

The first priming will be made by brush and covered with 0,8-1 kg/m² quartz-sand (0,4-0,7 mm) evenly . Loos sand-grains must be removed after curing of the coating . Afterwards apply the second priming coat by brush or role and cover with aggregate.

Work with falling temperatures in principle!

Air - and substrate-temperatures:

Minimally + 10°C, at least however + 3°C over the point of condensation,

At most + 25°C.

Relative humidity maximum. 80%

Precautions:

Component II of IPA PU-MEMBRANE / IPA PU-MEMBRANE viscous is corrosive!

Observe all protective measures prescribed by any competent social insurance association against occupational hazards in the chemical industry. Use gloves and protective goggles. Avoid any contact between the product and your skin. For improved protection, apply cream to your hands. Use a good deal of water to wash away any splashes of material reaching your skin or an eye; after-wards, immediately consult a physician

Processing-times:

	+10°C	+20°C	+ 25°C
IPA PU-MEMBRANE	approximately.	approximately.	approximately. 10.
IPA PU-MEMBRANE	40 min.'s.	15-20 min.'s.	Min.
VISCOUS			
Waiting time between the operations:			
	+ 10°C	+20°C	+ 30 °CS
IPAPOX B/DB	1 day	12 h.	6 h.
IPA PU MEMBRANE	3 days	2 days	1 day,
	From 4 hours	From 2 hours	From 2 hours

Respect: If the waiting time between prime coat and top coat are not respected, a reduced adhesion between the layers can occur.

Curing times:

Application of the Coating System	+10°C	+20°C	+ 30°C
Pedestrian use	Approx.. 6 hrs.	Approx.. 3 hrs	2 hrs
Vehicular use after	7 days	7 days	7 days

Cleaning of the equipment. IPA Aktivreiniger

Our application-technical consulting may support in word and writing your own work. It is intended as not binding advice. Product descriptions don't contain any declarations about liabilities for eventual damages. However, in case of any liability for damages, it is limited to the mere value of the delivered and used wares. With these data sheet all previous technical data about the product become invalid. Specifications of our collaborators, which are not in line of this data sheet require a written confirmation.

IPA Bauchemische Produkte GmbH Riedhof 5 – 82544 Egling – Tel. 08171-9990600 – Fax 08171-99906020 –

E-mail: info@IPA.de Internet: www.ipa.de oder www.ipanex.de